




GLENDALE

1 Color | 3 Sizes | 1 Finish



Light
COLOR



SIZES

SIZE:	600x600mm/24"x24"	800x800mm/32"x32"	600x1200mm/24"x48"
SURFACE:	Soft + Shaped	Soft + Shaped	Soft + Shaped
Light	MER6963	MER8963	MER12963









PACKING

Weight shown here may slightly vary depending on the production









Size Formate	Thickness Espesor	Box Caja			Pallet Paleta			Container/20' 24000Kg	Container/20' 27000Kg
cm	mm	pieces	m ²	kg	boxes	m ²	kg	m ² / sq.m	m ² / sq.m
60x60	9,5	4	1.44	30	40	57.6	1220	1127.52	1271.52
80x80	10	3	1.92	45	32	61.44	1460	1002.24	1130.88
60x120	11	2	1.44	35	56	80.64	1980	974.88	1097.28
inch	inch	units	ft ²	lb	boxes	ft ²	lb	ft ²	ft ²
23 5/8 x 23 5/8	3/8	4	15.50	66.14	40	620.00	2689.64	12136.52	13686.53
31 1/2 x 31 1/2	3/8	3	20.67	99.21	32	661.33	3218.75	10788.02	12172.69
23 5/8 x 47 1/4	7/16	2	15.50	77.16	56	868.00	4365.15	10493.52	11811.02

TECHNICAL FEATURES

This chart is for tiles with water absorption less than 0.5%, which is classified as impervious

Technical features	Standard	Standard requirement	Average value
Length and width		± 0.6%	± 0.3%
Thickness		± 5%	± 2%
 Straightness of sides	ISO 10545-2	± 0.5%	± 0.2%
Rectangularity		± 0.5%	± 0.2%
Surface flatness		± 0.5%	± 0.2%
 Water absorption	ISO 10545-3	≤0.5%	≤0.1%
Breaking strength		≥1300n	≥1500n
 Modulus of rupture	ISO 10545-4	≥35N/mm ²	≥39N/mm ²
 Abrasion resistance	ISO 10545-6	≤175 mm ²	Class 4
 Chemical resistance	ISO 10545-13	min class B	GLA
 Frost resistance	ISO 10545-12	required	Resistant
 Stain resistance	ISO 10545-14	min Class 3	Class 5
 Thermal shock resistance	ISO 10545-9	test method available	Resistant

This chart is for tiles with water absorption between 0.5% and 3%, which is classified as vitreous

Technical features	Standard	Standard requirement	Average value
Length and width		± 0.6%	± 0.3%
Thickness		± 5%	± 2%
 Straightness of sides	GB/T 3810.2	± 0.5%	± 0.3%
Rectangularity		± 0.5%	± 0.3%
Surface flatness		± 0.5%	± 0.3%
 Water absorption	GB/T 3810.3	$0.5\% < E \leq 3\%$	$E < 1.8\%$
 Breaking strength	GB/T 3810.4	$\geq 1100n$	$\geq 1500n$
Modulus of rupture		$\geq 30N/mm^2$	$\geq 35N/mm^2$
 Abrasion resistance	GB/T 3810.6	$\leq 175 mm^2$	Class 4
 Chemical resistance	GB/T 3810.13	indicated by the manufacturer	GLA
 Frost resistance	GB/T 3810.12	required	Resistant
 Stain resistance	GB/T 3810.14	min Class 3	Class 5
 Thermal shock resistance	GB/T 3810.9	test method available	Resistant



Made in China

MITO Ceramics belongs to Meiyitao (Fujian) High-tech Construction Materials Co., Ltd
www.mitoceramics.com | hello@mitoceramics.com | +86 13615963688

