

# LUMID GP1300A(W)

Injection Molding, PA6

## Description

General Purpose, High Viscosity

## Application

Industrial Material, Automotive, Others

Properties	Test Condition	Test Method	Unit	Typical Value
<b>Physical</b>				
Specific Gravity		ASTM D792	-	1.13
Molding Shrinkage		ASTM D955	%	1.0 ~ 1.4
Water Absorption	23 °C, 24hrs	ASTM D570	%	1.7
<b>Mechanical</b>				
Tensile Strength, 3.2mm @ Yield	50mm/min	ASTM D638	kg/cm <sup>2</sup>	780
Tensile Elongation, 3.2mm @ Break	50mm/min	ASTM D638	%	> 40
Flexural Strength, 6.4mm	2.8mm/min	ASTM D790	kg/cm <sup>2</sup>	1,050
Flexural Modulus, 6.4mm	2.8mm/min	ASTM D790	kg/cm <sup>2</sup>	26,000
IZOD Impact Strength, 6.4mm (Notched)	23 °C	ASTM D256	kg·cm/cm	4
Rockwell Hardness	R-Scale	ASTM D785	-	120
<b>Thermal</b>				
Melting Temperature		ASTM D3418	°C	220
Heat Deflection Temperature, 6.4mm	4.6kg	ASTM D648	°C	160

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23 °C, 50% relative humidity.

# LUMID GP1300A(W)

Injection Molding, PA6

## Description

General Purpose, High Viscosity

## Application

Industrial Material, Automotive, Others

## Electrical

Surface Resistivity		IEC 60093	Ohm	
Volume Resistivity	23℃	ASTM D257	Ohm·m	1.0E+15
Arc Resistance	23℃	ASTM D495	sec	195
Dielectric Strength, 1mm	23℃	ASTM D149	kV/mm	19
Dielectric Constant (10 <sup>6</sup> Hz)	23℃	ASTM D150	sec	3.5

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23℃, 50% relative humidity.

## Processing Guide (Injection Molding)

Processing Parameters		Unit	Value
Drying Temperature		℃	80 ~ 100
Drying Time		hrs	4 ~ 5
Maximum Moisture Content		%	0.1
Melt Temperature		℃	240 ~ 270
Cylinder Temperature	Rear	℃	225 ~ 245
	Middle	℃	230 ~ 260
	Front	℃	240 ~ 270
Nozzle Temperature		℃	240 ~ 270
Mold Temperature		℃	60 ~ 80
Back Pressure		kg/cm <sup>2</sup>	
Screw Speed		rpm	

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated : 17-Apr-18

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.